

TRUWHITE C2S FOLDING CARTON**PRODUCT SPECIFICATIONS**

Manufactured at Riegelwood, NC mill

Caliper	0.008	0.010	0.012	0.014	0.016	0.018	0.020	0.024
Nominal inches microns	203	254	305	356	406	457	508	610
Nominal Basis Weight, lbs/3MSF	120	144	165	188	203	220	2	286
Gsm	195	234	269	306	330	358	391	466
% Moisture	5.2	5.2	5.2	5.2	5.2	5.2	5.2	5.2
Brightness, Top side	94	94	94	94	94	94	94	94
Bottom side	94	94	94	94	94	94	94	94
Smoothness, Parker, Top Side	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
Bottom Side	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
Shade, b*	-4.5	-4.5	-4.5	-4.5	-4.5	-4.5	-4.5	-4.5
Goss, 75°, Top Side	65	65	65	65	65	65	65	65
Bottom Side	65	65	65	65	65	65	65	65
Stiffness, MD	30	60	110	150	200	220	230	470
CD	20	30	55	70	115	115	120	260
Tear, MD	140	180	225	240	240	300	320	655
CD	140	200	225	250	250	310	335	635

The above specifications are target values that describe the grades offered for sale, but are subject to change.